



TECHNICAL DATA SHEET

Compound :

HNBR

Copolymer acrylonitrile / butadiene

ORIGINAL PROPERTIES : Analysis on supplier laboratory compound

Physical-mechanical properties	Unit of measurement	Requested
Hardness	Shore A	50 ÷ 90
Density	g/cm ³	1,15 ÷ 1,50 *
Minimum temperature	° C	- 15 ÷ - 30 * (- 40) **
Maximum temperature	° C	150

Physical-mechanical characteristics	<p><i>Excellent mechanical properties</i></p> <p><i>Quite good resistance to permanent deformation</i></p> <p><i>Excellent abrasion-resistance</i></p> <p><i>Rebound elasticity from poor to high *</i></p>
-------------------------------------	---

Other properties	<p><i>Air and gas impermeability from good to excellent *</i></p> <p><i>Good UV radiation resistance</i></p> <p><i>Any flame resistance</i></p>
------------------	---

Chemical compatibility	<p><i>Excellent in contact with:</i></p> <ul style="list-style-type: none"> - Oils and mineral, vegetable and animal greases - Motor oils with mineral and sintetic basis at high temperatures - ATF oils - Aliphatic hydrocarbons * ** and fuels * ** - Water ** and saline solutions
	<p><i>Satisfactory in contact with:</i></p> <ul style="list-style-type: none"> - Ozone and atmospheric agents - Hydraulic fluids on the basis of fuel-oils amd from silicic esters - Different kinds of Freon - Alcohols (except the benzil) - Concentrated alkaline solutions up to 50°C *
	<p><i>Satisfactory enough in contact with:</i></p> <ul style="list-style-type: none"> - Diluted acid solutions - Xilene e toluene * ** - Sintetic lubricants on the basis of diesters
	<p><i>Insufficient in contact with:</i></p> <ul style="list-style-type: none"> - Strong concentrated mineral acids, hot diluted alkaline solutions - Different brake fluids on the basis of not fuel-oils - Ketones and esters - Benzene and chloridated hydrocarbons - Hydraulic fluids on the basis of phosphoric esters - Phenol

*depending from the types

** with a specific optimal formulation