



TECHNICAL DATA SHEET

Compound :	NBR Maroon	Copolymer acrylonitrile / butadiene (with percentage of ACN from 18% up to 50% approx.)
Base fabric type:	Cotton	

ORIGINAL PROPERTIES : Analysis on supplier laboratory compound

Physical-mechanical properties	Unit of measurement	Requested
Hardness	Shore A	90
Elongation at break	N/5cm	450 ÷ 500
Minimum temperature	° C	- 15 ÷ - 30
Maximum temperature	° C	100 ÷ 110 (130)

Physical-mechanical characteristics	<p><i>Excellent mechanical properties</i></p> <p><i>Good resistance to permanent deformation</i></p> <p><i>Good abrasion resistance</i></p>
-------------------------------------	---

Other properties	<p><i>Absence of toxicity</i></p> <p><i>Good dyeing</i></p> <p><i>Air and gas impermeability from good to excellent</i></p> <p><i>Poor UV radiation resistance</i></p> <p><i>Any flame resistance</i></p> <p><i>Poor dielectric properties</i></p>
------------------	--

Chemical compatibility	<p><i>Excellent in contact with:</i></p> <ul style="list-style-type: none"> - Oils and mineral, vegetable and animal greases - Aliphatics hydrocarbons and fuels - Water and saline solutions
	<p><i>Satisfactory in contact with:</i></p> <ul style="list-style-type: none"> - Hydraulic fluids on the basis of fuel-oils and of sillicic esters - Different kinds of freon - Alcohols (except the benzil) - Concentrated alkaline solutions up to 50°C
	<p><i>Satisfactory enough in contact with:</i></p> <ul style="list-style-type: none"> - Diluted acid solutions - Xilene and toluene - Sintetic lubricants on the basis of diesters
	<p><i>Insufficient in contact with:</i></p> <ul style="list-style-type: none"> - Strong concentrated mineral acids, hot diluited alkaline solutions - Ozone and atmospheric agents (except with formulations containing protective agents) - Different brake fluids on the basis of not fuel-oils - Ketones and esters - Benzene and chloridated hydrocarbons - Hydraulic fluids on the basis of phosphoric esters - Phenol

* depending from the types

** with a specific optimal formulation